



Pulbere metalica

Pulberea metalica este fabricata din sarma din otel si sarma de otel inox trasa la rece cu diametrul de 3.1 mm si continut scazut de carbon.

Detalii tehnice

Compozitie chimica: C: 0.07 ÷ 0.12
(%) Mn: 0.60 ÷ 1.00
Si: 0.08 ÷ 0.13
P: < 0.05
S: < 0.05

Analiza granulometrica

Marimea ochiului intern al sitei (mm)	Repartitia particulelor pe baza marimii
2.000	0
1.000	3
0.500	7
0.250	15
0.125	10
<0.125	65

Proprietati fizice:

Densitate specifica (g/ccm)	7.8
Volum aparent (ccm/100g)	205
Volum comprimat (ccm/100g)	140
Extract acetonic (%)	0.15

Ambalare: in saci de hartie de 25 kg, 40 saci asezati pe paleti din lemn de 1 tm ,
impachetati in folie de polipropilena.

Productie anuala : 500 to